

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE

2

REPORT DOCUMENTATION PAGE

Form Approved
OMB No 0704-0188

AD-A225 004

1b. RESTRICTIVE MARKINGS

3. DISTRIBUTION / AVAILABILITY OF REPORT
Approved for Public Release
Distribution Unlimited

4. PERFORMING ORGANIZATION REPORT NUMBER(S)

5. MONITORING ORGANIZATION REPORT NUMBER(S)

6a. NAME OF PERFORMING ORGANIZATION
Department of Chemistry
University of North Carolina6b. OFFICE SYMBOL
(If applicable)7a. NAME OF MONITORING ORGANIZATION
Office of Naval Research6c. ADDRESS (City, State, and ZIP Code)
Campus Box 3290
Chapel Hill, NC 27599-32907b. ADDRESS (City, State, and ZIP Code)
Department of the Navy
Arlington, VA 222178a. NAME OF FUNDING / SPONSORING
ORGANIZATION8b. OFFICE SYMBOL
(If applicable)9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER
N0014-89-J-1734

8c. ADDRESS (City, State, and ZIP Code)

10. SOURCE OF FUNDING NUMBERS

PROGRAM
ELEMENT NO.PROJECT
NO.TASK
NO.WORK UNIT
ACCESSION NO.11. TITLE (Include Security Classification) UNCLASSIFIED: Bis(Phthalocyaninato) Lanthanide
Sandwich Compounds Exhibiting Mixed Valence Ligands12. PERSONAL AUTHOR(S) Kathleen L. Trojan, William E. Hatfield, Keith D. Kepler,
and Martin L. Kirk13a. TYPE OF REPORT
Technical Report13b. TIME COVERED
FROM _____ TO _____14. DATE OF REPORT (Year, Month, Day)
July 13, 199015. PAGE COUNT
11

16. SUPPLEMENTARY NOTATION

Technical Report No. 38

17. COSATI CODES

FIELD

GROUP

SUB-GROUP

18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)
lanthanide/ytterbium/thulium/phthalocyanine/magnetic
susceptibility/ electron paramagnetic resonance/ electronic
spectroscopy/intervalence charge transfer. DTIC

19. ABSTRACT (Continue on reverse if necessary and identify by block number)

Bis(phthalocyaninato) lanthanide sandwich compounds have been synthesized for ytterbium and thulium. Low temperature magnetic susceptibility data suggest a strong antiferromagnetic interaction between the lanthanide f-electrons and the phthalocyaninato ligand radical electron.

20. DISTRIBUTION / AVAILABILITY OF ABSTRACT

☐ UNCLASSIFIED/UNLIMITED ☐ SAME AS RPT ☐ DTIC USERS

21. ABSTRACT SECURITY CLASSIFICATION

UNCLASSIFIED

22a. NAME OF RESPONSIBLE INDIVIDUAL

22b. TELEPHONE (Include Area Code)

22c. OFFICE SYMBOL

90 07 16 218

OFFICE OF NAVAL RESERACH

Contract N0014-89-J-1734

R&T Code 4135007---05

TECHNICAL REPORT NO. 38

A-1

BIS(PHTHALOCYANINATO) LANTHANIDE SANDWICH COMPOUNDS
EXHIBITING MIXED VALENCE LIGANDS

by

Kathleen L. Trojan, William E. Hatfield,
Keith D. Kepler and Martin L. Kirk

The Department of Chemistry, The University of North
Carolina at Chapel Hill, North Carolina, 27599, U.S.A.

Prepared for Publication in

NATO ASI SERIES

Mixed Valency Systems: Applications in Chemistry,
Physics and Biology

Reproduction in whole or in part is permitted for
any purpose of the United States Government

*This document has been approved for public release
and sale, its distribution is unlimited.

*This statement should also appear in Item 3 of Document Control
Data - DD Form 1473. Copies of the form are available from the
cognizant contract administrator.

BIS(PHTHALOCYANINATO) LANTHANIDE SANDWICH COMPOUNDS EXHIBITING MIXED VALENCE LIGANDS

Kathleen L. Trojan, William E. Hatfield, Keith D. Kepler and
Martin L. Kirk
Department of Chemistry
The University of North Carolina
Chapel Hill, N.C. 27599-3290 USA

ABSTRACT. Bis(phthalocyaninato) lanthanide sandwich compounds have been synthesized for ytterbium and thulium. Low temperature magnetic susceptibility data suggest a strong antiferromagnetic interaction between the lanthanide *f*-electrons and the phthalocyaninato ligand radical electron.

Introduction

Lanthanide sandwich compounds with the formula $\text{Ln}(\text{Pc})_2$ have been known for over twenty-five years [1]. To a first approximation, the lanthanide ion has a formal oxidation state of +3, with one of the phthalocyanine ligands having a charge of -2, while the second phthalocyanine ligand is a singly oxidized radical with a charge of -1. The crystal structure of $[\text{Lu}(\text{Pc})_2] \cdot \text{CH}_2\text{Cl}_2$ has been determined by Weiss et. al. [2] Other lanthanide sandwich compounds have essentially the same structure [3] in which the two phthalocyaninato rings are rotated an average of 45° with respect to one another, and it is assumed that the compounds described here have the same structure. Powdered samples of the compounds used in this study were verified by their ultraviolet, visible and near-infrared spectra and by elemental analysis. This paper will focus on the ytterbium and thulium bisphthalocyaninato sandwich compounds.

Experimental

Ultra-violet and visible spectra from 300 to 800 nm were collected on a Hewlett Packard Diode Array spectrophotometer at room temperature in CH_2Cl_2 solution. The near-infrared data from 750 to 1650 nm were collected

on a Cary-17 spectrophotometer at room temperature in CH_2Cl_2 solution. Magnetic susceptibility data of powdered samples were collected by using a Princeton Applied Research Model 155 vibrating sample magnetometer (VSM) equipped with a Janis Research Co. liquid helium cryostat. The magnetometer was calibrated using $\text{HgCo}(\text{NCS})_4$ [4]. Data were collected in the temperature range 4.2-120 K with a magnetic field of 1 kOe for Tm and 8 kOe for Yb. The data were corrected to compensate for the diamagnetism of the constituent atoms [5].

Results and Discussion

The ultraviolet, visible spectra of $\text{Yb}(\text{Pc})_2$ and $\text{Tm}(\text{Pc})_2$ show a Soret band at 320 nm and a Q band at 660 nm (figure 1) typical of phthalocyanine in its dianionic state [6]. The visible and near infrared spectra (figure 2) show a band at 458 nm (Yb) or 460 nm (Tm) and at 917 nm (Yb) or 915 nm (Tm), which correspond to the $2e_g(\pi) \rightarrow 1a_{1u}(\pi)$ and $1e_g(\pi) \rightarrow 1a_{1u}(\pi)$, respectively. These transitions are typical for phthalocyanine in its monoanionic state, due to the "missing" electron in the a_{1u} orbital [7]. The near infrared spectra also show a transition (figure 2) at 1386 nm (Yb) or at 1390 nm (Tm) which has been assigned to an intervalence charge transfer band [8], where the dianionic phthalocyanine acts as the donor and the monoanion acts as the acceptor.

Low temperature magnetic susceptibility data for these compounds reflect a strong antiferromagnetic interaction between the lanthanide f-electrons and the phthalocyaninato ligand radical electron. This antiferromagnetic coupling leads to a reduction of both the free ion spin multiplicity and the J-value of the free ion term. Normally, J is a good quantum number for most of the lanthanide ions [9] (except Eu and Sm), and large spin-orbit coupling causes J to J' separations which are much larger than the crystal field. In such cases, only the ground state is populated and the Landé g factor is given by:

$$g = 1 + \frac{[S(S+1) - L(L+1) + J(J+1)]}{2J(J+1)}.$$

However, due to the coupling of the lanthanide f-electrons with the radical electron, two new states arise from the spin-orbit ground state (figure 3).

In the case of $\text{Tm}(\text{Pc})_2$ the free ion ground state term symbol is $^3\text{H}_6$ and from the equation

$$\mu_{\text{eff}} = g [J(J+1)]^{1/2},$$

a limiting moment of 7.6 B.M. is expected. The experimental magnetic susceptibility data for $\text{Tm}(\text{Pc})_2$ (figure 4) taken from 4.2 to 120 K appears to follow the Curie-Weiss law up to approximately 65 K where the moment




Figure 1: Ultraviolet and visible spectrum from 300 to 800 nm for Tm(Pc)_2 and Yb(Pc)_2 in CH_2Cl_2 .




Figure 2: Near-infrared spectra for Tm(Pc)_2 (top) and Yb(Pc)_2 (bottom) from 750 to 1650 nm in CH_2Cl_2 .

begins to level off at ~6.6 B.M. Above 65 K the susceptibility data appears to deviate from this behavior. The coupled terms which arise from the 3H_6 free ion ground term are a $^2H_{11/2}$ antiferromagnetically coupled term and a $^4H_{13/2}$ ferromagnetically coupled term. Initially assuming that only the $^2H_{11/2}$ state is populated, a Landé g-factor of 1.09 and a limiting moment of 6.5 B.M. is expected. An attempt to fit the data to the Curie-Weiss Law appears to model the data only up to ~65 K and gave a g value of 1.17 which gives only fair agreement with the theoretical value.

In the case of $Yb(Pc)_2$ the free ion ground state term symbol is $^2F_{7/2}$ and a limiting moment of 4.5 B.M. is expected. The experimental magnetic susceptibility data (figure 4) shows a leveling off of the moment of ~3.6 B.M. from ~30 to 55 K which again begins to show deviations from the Curie-Weiss law above 55 K. The coupled terms which arise from the $^2F_{7/2}$ free ion ground term (as shown in figure 3) are a 1F_3 antiferromagnetically coupled term and a 3F_4 ferromagnetically coupled term. Initially assuming that only the 1F_3 state is populated, a Landé g-factor of 1.00 is expected with a limiting moment of 3.5 B.M. An attempt to fit the data to the Curie-Weiss Law appears to model the data only up to ~55 K and gave a g value of 1.09 which also gives only fair agreement with the theoretical value.

It is apparent that this deviation from the Curie-Weiss Law is due to the presence of the low-lying higher spin multiplicity component arising from the exchange coupling. From the Van Vleck equation

$$\chi = \frac{N \sum_n \left[\frac{E_n^{(1)2}}{kT} - 2E_n^{(0)} \right] \exp\left(\frac{-E_n^{(0)}}{kT}\right)}{\sum_n B_n \exp\left(\frac{-E_n^{(0)}}{kT}\right)}$$

when the energy of the antiferromagnetically coupled ground state $E_0^{(0)}$ is arbitrarily set equal to zero, the energy of the ferromagnetically coupled excited state $E_1^{(0)}$ is defined as ΔE , the first order zeeman energies are defined as $E_n^{(1)} = m_j g_j \beta$ and second order (and higher) effects are neglected, a simple expression can be derived to express the behavior of the magnetic susceptibility in these systems which is of the form:




Figure 3: Schematic energy level diagram for the lanthanide, phthalocyaninato- radical coupled complex with ytterbium as the example.




Figure 4: Magnetic susceptibility data for the bis(phthalocyaninato)-lanthanide(III) sandwich compounds. Experimental points are shown as '+'s and best fit lines for the Curie-Weiss and VanVleck expressions are drawn (see text).

$$\chi = \frac{N\beta^2}{kT} \left\{ \frac{\sum_j (m_j g_j)^2 + \sum_j (m_j g_j)^2 \exp\left(\frac{-\Delta E}{kT}\right)}{(2J_0+1) + (2J_1+1) \exp\left(\frac{-\Delta E}{kT}\right)} \right\}$$

When this equation, including the presence of both states, is fit to the data, excellent agreement is obtained for both the ground and excited states. For $\text{Tm}(\text{Pc})_2$, $g(^2\text{H}_{11/2})_{\text{calc}} = 1.09$, $g(^2\text{H}_{11/2})_{\text{exp}} = 1.10$ and $g(^4\text{H}_{13/2})_{\text{calc}} = 1.23$, $g(^4\text{H}_{13/2})_{\text{exp}} = 1.21$ with a 106 cm^{-1} energy separation between states. Similarly, for $\text{Yb}(\text{Pc})_2$, $g(^1\text{F}_3)_{\text{calc}} = 1.00$, $g(^1\text{F}_3)_{\text{exp}} = 0.95$ and $g(^3\text{F}_4)_{\text{calc}} = 1.25$, $g(^3\text{F}_4)_{\text{exp}} = 1.25$ with a 125 cm^{-1} energy separation between states.

In the figure of μ_{eff} vs. temperature (figure 4), the data points are shown as +s. The solid lines drawn through the data points were generated by the Van Vleck equation with the parameters given above. The best fit Curie-Weiss lines are shown for comparison.

X-band EPR measurements from 0 to 8000 Oe at ambient and lower temperatures show no transitions at or near $g=2$, which would have been indicative of a free radical. The absence of a signal is due to the strong coupling between the phthalocyaninato ligand radical electron and the f-electron. At room temperature, both $\text{Yb}(\text{Pc})_2$ and $\text{Tm}(\text{Pc})_2$ are EPR silent. At 12.7 K, $\text{Yb}(\text{Pc})_2$ shows two transitions at $g_1 = 4.34$ and $g_2 = 9.42$, while $\text{Tm}(\text{Pc})_2$ at 7.2 K exhibits a very complicated spectrum with several transitions. The EPR spectrum of $\text{Lu}(\text{Pc})_2$, which contains no unpaired f-electrons, exhibits the free radical transition at $g = 2.00$ at both 7.2 and 298 K.

It is apparent from the EPR spectra, reduction of the moment from the free ion value and excellent agreement of the experimental data with the Van Vleck model derived for these systems that a strong coupling exists between the phthalocyaninato ligand radical electron and the f-electrons for $\text{Tm}(\text{Pc})_2$ and $\text{Yb}(\text{Pc})_2$. It should be noted that $\text{Yb}(\text{Pc})_2$ with a $^1\text{F}_3$ ground term and a magnetic moment of 3.6 B.M. is the first example of a complex compound in which magnetism is solely attributed to orbital angular momentum.

Acknowledgement

This work was supported in part by the Office of Naval Research.

References

- (1) (a) Moskalev, P.N.; Kirin, I.S. *Russian J. Inorg. Chem.* 1970, 15(1), 7. (b) Moskalev, P.N.; Kirin, I.S. ; Makashev, Y.A. *Russian J. Inorg. Chem.* 1965, 10(8), 1065.
- (2) Decian, A.; Moussavi, M.; Fischer, J.; Weiss, R. *Inorg. Chem.* 1985, 24, 3162.
- (3) (a) Gieren, A.; Hoppe, W. *Chem. Comm.* 1971, 413. (b) Kasuga, K.; Tsutsui, M.; Petterson, R.C.; Tatsumi, K.; Van Opdenbosch, N.; Pepe, G.; Meyer, E.F., Jr. *J. Amer. Chem. Soc.* 1980, 102, 4836. (c) Darovskikh, A.N., private communications.
- (4) Brown, D.B.; Crawford, V.H.; Hall, J.W.; Hatfield, W.E. *J. Phys. Chem.* 1977, 81, 1303.
- (5) (a) Figgis, B.N.; Lewis, J. In Modern Coordination Chemistry; Lewis, J.; Williams, R.G., Eds.; Interscience: New York; 1960; p. 403.
- (6) Minor, P.C.; Gouterman, M.; Lever, A.B.P. *Inorg. Chem.* 1985, 24, 1894.
- (7) (a) Sugimoto, H.; Higashi, T.; Mori, M. *J. Chem. Soc. Chem. Commun.* 1983, 622. (b) Turek, P.; André, J.J.; Giraudeau, J.; Simon, J. *Chem. Phys. Letters* 1987, 134, 471.
- (8) Markovitsi, D.; Tran-Thi, T.-H.; Even, R.; Simon, J. *Chem. Phys. Letters* 1987, 137(2), 107.
- (9) Siddall, T. H. In Theory and Applications of Molecular Paramagnetism; Boudreaux, E. A. ; Mulay, L. N., Eds.; Wiley: New York, 1976; pp. 257.

TECHNICAL REPORT DISTRIBUTION LIST, GENERAL

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Chemistry Division, Code 1113 800 North Quincy Street Arlington, VA 22217-5000	3	Dr. Ronald L. Atkins Chemistry Division (Code 385) Naval Weapons Center China Lake, CA 93555-6001	1
Commanding Officer Naval Weapons Support Center Attn: Dr. Bernard E. Doua Crane, IN 47522-5050	1	Chief of Naval Research Special Assistant for Marine Corps Matters Code OOMC 800 North Quincy Street Arlington, VA 22217-5000	1
Dr. Richard W. Drisko Naval Civil Engineering Laboratory Code L52 Port Hueneme, California 93043	1	Dr. Bernadette Eichinger Naval Ship Systems Engineering Station Code 053 Philadelphia Naval Base Philadelphia, PA 19112	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	2 <u>high</u> <u>quality</u>	Dr. Sachio Yamamoto Naval Ocean Systems Center Code 52 San Diego, CA 92152-5000	1
David Taylor Research Center Dr. Eugene C. Fischer Annapolis, MD 21402-5067	1	David Taylor Research Center Dr. Harold H. Singerman Annapolis, MD 21402-5067 ATTN: Code 283	1
Dr. James S. Murday Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375-5000	1		

ORGANOELEMENT CHEMISTRY - Distribution List

Professor O. T. Beachley, Jr.
Department of Chemistry
State University of New York
Buffalo, NY 14214
R&T Code 4135002

Professor Herbert C. Brown
Purdue University
Department of Chemistry
West Lafayette, IN 47907
R&T Code 4135011

Professor Steven L. Buchwald
Department of Chemistry
Massachusetts Institute of Technology
Cambridge, MA 02139
R&T Code 4135014

Professor William E. Hatfield
Department of Chemistry
University of North Carolina
Chapel Hill, NC 27514
R&T Code 4135007

Professor M. Frederick Hawthorne
Department of Chemistry
405 Hilgard Avenue
University of California
Los Angeles, CA 90024
R&T Code 4135004

Professor Robert H. Neilson
Department of Chemistry
Texas Christian University
Fort Worth, TX 76843
R&T Code 4135005

Professor Kurt Niedenzu
Department of Chemistry
University of Kentucky
Lexington, KY 40506
R&T Code 4135003

Professor Richard L. Wells
Department of Chemistry
Duke University
Durham, NC 27706
R&T Code 4135008